IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re: Hippolit Gstrein et al; Serial No.: not yet assigned Filed: concurrently herewith For: PAPERMAKER'S FELT

Date: August 20, 2001

Commissioner for Patents Washington, DC 20231

PRELIMINARY AMENDMENT

Sir:

Applicants provide the present Preliminary Amendment as part of a Application in the present case. Attached hereto is a marked-up version of the changes made to the claims and the specification by the current amendment. The marked up version of the changes is captioned "Version With Markings To Show Changes Made."

In the Specification:

Please correct the title "Felt" to read -- PAPERMAKER'S FELT--.

At page 1, line 1, please insert

-- Claim for Priority and Cross-Reference to Other Applications

This application claims priority to German Application No. 100 40 828.1, filed August 21, 2000, the disclosure of which is hereby incorporated herein by reference. -

Page 1, line 10, please delete the heading "DESCRIPTION" and substitute therefor --Field of the Invention --.

Page 1, line 15, please insert -- Background of the Invention --.

Page 2, line 22, please insert -- Summary of the Invention --.

Page 2 of 5

Page 2, line 27, please delete "This objective is achieved by a felt with the characteristics given in Claim 1."

Page 7, line 17, please insert the heading -- Brief Description of the Figures --.

Page 7, line 27, please insert the heading --<u>Detailed Description of the Invention</u> --.

In the Claims:

Please amend the claims as follows:

- 8. (Amended) Felt according to claim 1, characterized in that monofils (110) used to form the twisted structure have a diameter in the range from 0.1 mm to 0.9 mm.
- 9. (Amended) Felt according to claim 1, characterized in that the twisted structure (10) has a mean outside diameter in the range from 0.3 mm to 1.0 mm.
- 10. (Amended) Felt according to claim 1, characterized by a transverse-thread density above 130 transverse threads per 10 cm.

REMARKS

Applicants provide the present Preliminary Amendment concurrent with the filing of the present application to comply with the requirements of the United States Patent and Trademark Office.

Respectfully submitted,

James R. Cannon

Registration No. 38,539

Page 3 of 5

Correspondence Address:

20792 PATENT TRADEMARK OFFICE

CERTIFICATE OF EXPRESS MAILING

Express Mail Label No. EL 920739682 US

Date of Deposit: August 20, 2001

I hereby certify that this correspondence is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to: BOX Patent Application, Commissioner for Patents, Washington, DC 20231.

Joyce Paoli Date of Signature: August 20, 2001

Page 4 of 5

VERSION WITH MARKINGS TO SHOW CHANGES MADE

In the Specification:

Please correct the title "Felt" to read -- PAPERMAKER'S FELT--.

At page 1, line 1, please insert.

-- Claim for Priority and Cross-Reference to Other Applications

This application claims priority to German Application No. 100 40 828.1, filed August 21, 2000, the disclosure of which is hereby incorporated herein by reference. -

Page 1, line 10, please delete the heading "DESCRIPTION" and substitute therefor -- Field of the Invention --.

Page 1, line 15, please insert -- Background of the Invention --.

Page 2, line 22, please insert -- Summary of the Invention --.

Page 2, line 27, please delete "This objective is achieved by a felt with the characteristics given in Claim 1."

Page 7, line 17, please insert the heading -- Brief Description of the Figures --

Page 7, line 27, please insert the heading --<u>Detailed Description of the</u> Invention --.

In the Claims:

Please amend the claims as follows:

Claim 8. (Amended) Felt according to claim 1, characterized in that monofils (110) used to form the twisted structure have a diameter in the range from 0.1 mm to

Page 5 of 5

0.9 mm[, preferably in the range from 0.1 mm to 0.5 mm and especially preferably in the range from 0.1 mm to 0.3 mm].

Claim 9. (Amended) Felt according to claim 1, characterized in that the twisted structure (10) has a mean outside diameter in the range from 0.3 mm to 1.0 mm[, preferably in the range from 0.4 mm to 0.8 mm and especially preferably in the range from 0.4 mm to 0.6 mm].

Claim 10. (Amended) Felt according to claim 1, characterized by a transverse-thread density above 130 transverse threads per 10 cm[, preferably in the range from 130 to 200 transverse threads per 10 cm and especially preferably in the range from 140 to 180 transverse threads per 10 cm].